TENNIS SURFACES

Plush™

6gal. PLUSHPATCH BINDER KIT

ACRYLIC CRACK AND LEVELING COMPOUND

Item#:3030

UPC#:090932030305

APPLICATION GUIDE

Description and Usage

An acrylic emulsion mixed at the jobsite to repair cracks or “birdbaths” in recreational blacktop tennis and/or basketball courts. A three component system, the Plushpatch Binder Kit is an acrylic crack and leveling Compound is used to fill and level both surface and structural cracks, as well as “birdbaths.” Prior to the application of the Plush Acrylic Color System, thoroughly clean all cracks and apply the Leveling Compound. When used for “birdbath” patching, thoroughly clean the area to be leveled.

Application

Apply directly into clean, dry cracks with a steel hand trowel.

For leveling “birdbaths” use a rubber faced squeegee or straight edge.

NOTE: Allow 24 hours curing time before applying additional coatings.

Mix Design

Latex•ite Acrylic Crack and Leveling Compound	1 Gallon
80-100 mesh, clean dry Silica Sand	2 Gallons
Portland 1A Cement	1/4 Gallon

Never Add Water

Clean equipment and tools immediately after completion.

Coverage

CRACK: One (1) gallon of mixed emulsion. Approximately 8-10 linear feet of crack measuring 1/4” wide by 3/4” wide to 1” deep.

PATCH: Quantities will vary with size and depth of “birdbath”.

Drying Time

Mixed material dries rapidly. Actual drying time will vary according to width and depth of crack or patch. Humidity, surface temperature, and ambient temperature will affect drying process. We recommend allowing for full cure prior to coating over (overnight in nice weather, 24 hours if shaded or cooler).

Limitations and Precautions

The Plushpatch binder kit should not be applied when the ambient temperature is below 50º F or when surface temperature is above 140º F. Do not store in direct sunlight. Keep from freezing. Do not apply when rain is imminent.

DALTON™ ENTERPRISES, INC.

Copyright ©4/2012